



ULTRA SPEC® HP

D.T.M. ACRYLIC SEMI-GLOSS

FP29

Features

- Direct to metal application
- Self-priming
- Excellent adhesion
- Improved gloss & colour retention
- Fast dry and recoat times
- Corrosion resistant
- Easy application
- Semi-gloss finish

Recommended For

Ferrous or non-ferrous metal, Bilco® doors, railings, structural or support steel, wood, masonry surfaces, bar joists, equipment, roof vents, fencing, metal storage sheds and general maintenance painting interior or exterior surfaces

General Description

This product is designed to perform a dual purpose as a direct to metal primer and finish. Both coats of the product provide rust inhibition for superior corrosion control. The acrylic formula provides excellent gloss and colour retention. The film is fast drying permitting fast recoat. This product is also an excellent finish for masonry, plaster, wallboard and interior wood surfaces.

Limitations

- Do not apply when air and surface temperatures are below 10 °C (50 °F).
- Not for floor applications.
- Not for exposure to strong chemicals.

Product Information

Colours — Standard: Safety White (08), Safety Yellow (15), Safety Red (21), Safety Black (82)	<table border="1"> <thead> <tr> <th colspan="2">Technical Data[◇]</th> <th>Base 1</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">Titanium Dioxide & Corrosion Inhibitors</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>46 %</td> </tr> <tr> <td>Coverage per Gallon at</td> <td></td> <td>27.8 – 37.2 Sq. m</td> </tr> <tr> <td>Recommended Film Thickness</td> <td></td> <td>(300 – 400 Sq. Ft.)</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>4.0 – 5.4 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.8 – 2.5 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– To Touch</td> <td>1 Hour</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Coalescence</td> </tr> <tr> <td>Dry Heat Resistance</td> <td></td> <td>121.1 °C (250 °F)</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>77 ± 4 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>None</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Semi-Gloss (45 – 55 @ 60°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>10 °C (50 °F)</td> </tr> <tr> <td></td> <td>– Max</td> <td>37.8 °C (100 °F)</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Clean Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td></td> <td>4 kg (10.2 lbs)</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>4.4 °C (40 °F)</td> </tr> <tr> <td></td> <td>– Max</td> <td>32.2 °C (90 °F)</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="3" style="text-align: center;">148 Grams/Litre</td> </tr> </tbody> </table>	Technical Data [◇]		Base 1	Vehicle Type		Acrylic	Pigment Type	Titanium Dioxide & Corrosion Inhibitors		Volume Solids		46 %	Coverage per Gallon at		27.8 – 37.2 Sq. m	Recommended Film Thickness		(300 – 400 Sq. Ft.)	Recommended Film Thickness	– Wet	4.0 – 5.4 mils		– Dry	1.8 – 2.5 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.			Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour		– To Recoat	4 Hours	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Coalescence	Dry Heat Resistance		121.1 °C (250 °F)	Viscosity		77 ± 4 KU	Flash Point		None	Gloss / Sheen		Semi-Gloss (45 – 55 @ 60°)	Surface Temperature at Application	– Min.	10 °C (50 °F)		– Max	37.8 °C (100 °F)	Thin With		Clean Water	Clean Up Thinner		Clean Water	Weight Per Gallon		4 kg (10.2 lbs)	Storage Temperature	– Min.	4.4 °C (40 °F)		– Max	32.2 °C (90 °F)	Volatile Organic Compounds (VOC)			148 Grams/Litre		
Technical Data [◇]		Base 1																																																																													
Vehicle Type		Acrylic																																																																													
Pigment Type	Titanium Dioxide & Corrosion Inhibitors																																																																														
Volume Solids		46 %																																																																													
Coverage per Gallon at		27.8 – 37.2 Sq. m																																																																													
Recommended Film Thickness		(300 – 400 Sq. Ft.)																																																																													
Recommended Film Thickness	– Wet	4.0 – 5.4 mils																																																																													
	– Dry	1.8 – 2.5 mils																																																																													
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.																																																																															
Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour																																																																													
	– To Recoat	4 Hours																																																																													
Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																															
Dries By		Coalescence																																																																													
Dry Heat Resistance		121.1 °C (250 °F)																																																																													
Viscosity		77 ± 4 KU																																																																													
Flash Point		None																																																																													
Gloss / Sheen		Semi-Gloss (45 – 55 @ 60°)																																																																													
Surface Temperature at Application	– Min.	10 °C (50 °F)																																																																													
	– Max	37.8 °C (100 °F)																																																																													
Thin With		Clean Water																																																																													
Clean Up Thinner		Clean Water																																																																													
Weight Per Gallon		4 kg (10.2 lbs)																																																																													
Storage Temperature	– Min.	4.4 °C (40 °F)																																																																													
	– Max	32.2 °C (90 °F)																																																																													
Volatile Organic Compounds (VOC)																																																																															
148 Grams/Litre																																																																															
— Tint Bases: Benjamin Moore® Gennex® bases 1X, 2X, 3X & 4X																																																																															
— Special Colours: Contact your Benjamin Moore® representative.																																																																															
Certifications & Qualifications: VOC compliant in all regulated areas Qualifies for LEED® v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified Master Painters Institute MPI # 141, 153, 163 Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84																																																																															
Customer Information Centre: 1-800-361-5898, info@benjaminmoore.ca , www.benjaminmoore.ca																																																																															

◇Reported values are for Base 1

Surface Preparation

Surfaces to be coated must be clean, dry, and free of oil, grease, dust, flaky rust, mill scale, loose paint, chalk, and other foreign matter than could interfere with adhesion. Glossy surfaces should be dulled by abrading the surface.

Metal: Remove loose rust and scale with a scraper, wire brush, or sandpaper. Remove oils from bare metal with an Oil & Grease Emulsifier Corotech® V600.

Wood: Spot-prime patched and spackled areas with this product or any recommended Benjamin Moore® primer before and after repairing. Protected exterior areas such as eaves, ceilings, and overhangs should be washed with detergent solution and rinsed with a strong stream of water from a garden hose to remove surface salts that can interfere with proper adhesion.

Mildew: Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (K318) prior to coating the surface.

Caution: Refer to the (K318) Clean technical data and safety data sheets for instructions on its proper use and handling.

Difficult Substrates: Benjamin Moore® offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Primer/Finish Systems

Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29) is self-priming on properly prepared ferrous and non-ferrous metal substrates. New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your Benjamin Moore® retailer.

Ferrous Metal Surfaces (Iron & Steel):

Finish: 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Non-Ferrous Metal (Galvanized & Aluminum):

All new non-ferrous metal surfaces must be thoroughly cleaned with an Oil & Grease Emulsifier Corotech® V600 to remove contaminants

Finish: 1 or 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Masonry, Smooth Poured or Precast Concrete:

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Masonry, Rough or Pitted:

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571)

Finish: 1 or 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Plaster and Wallboard:

All plaster surfaces must be thoroughly cured for at least 30 days.

Drywall surfaces must be free of sanding dust.

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Wood, and engineered wood products:

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Multi-Purpose Oil Based Primer (F024) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (K046) may be used

Finish: 1 or 2 coats Ultra Spec® HP D.T.M. Acrylic Semi-Gloss (FP29)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Mixing of Paint: Stir thoroughly before and occasionally during use. For best application results, apply generously going from unpainted into painted areas. A one-coat application protects and preserves; two coats provides greater durability. Apply with an all-purpose synthetic brush, short nap roller, or spray.

Spray, Airless: Fluid Pressure — 1,500 to 2,500 PSI;
.013 - .017 Orifice

Thinning/Clean Up

Thinning: Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents. Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Clean Up: Clean all equipment immediately after using with soap and water. Spray equipment should be given a final rinse with mineral spirits to prevent corrosion or follow state/local guidelines on solvent use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**