



# ACRYLIC METAL PRIMER V110

## Features

- High solids
- Suitable for occupied areas
- Can be recoated in just 4 hours
- Suitable For Use In USDA Inspected Facilities

## Recommended For

Carbon Steel, Iron, Aluminum, Galvanized, Other Non-Ferrous Metals, Glass, Lexan, Concrete, Drywall. Acrylic Metal Primer is designed for use in general metal finishing/fabrication, food/beverage processing, chemical processing, industrial maintenance/refurbishment, and other segments where a rust inhibitive water cleanup primer is necessary.

## General Description

Acrylic Metal Primer is a water-reducible, rust-inhibitive primer for steel, iron, and non-ferrous metal. It provides excellent adhesion to a range of hard-to-coat surfaces and can even be applied over tightly adhering rust. Designed for light-to-moderate industrial exposures, this product can be top coated with a wide variety of coatings.

## Limitations

- Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C). Relative humidity should be below 90%.
- Do not apply if within 5 degrees of dew point or if rain is expected within 12 hours of application.
- Not for immersion service. Not for use on floors.
- Not for use on Kynar unless tested and approved by user.

## Product Information

### Colors — Standard:

White (01), Red (20)  
Can be tinted with up to 2oz. Universal Colorants

### — Tint Bases:

N/A

### — Special Colors:

Contact your retailer.

### Certification & Qualifications :

Suitable for use in USDA inspected facilities  
Meets Performance Requirements of TT-P-1975 and MIL-P-28577  
Meets SSPC Paint #23

VOC REGION	COMPLIANT
FEDERAL	YES
OTC	YES
OTCII	YES
CARB	YES
CARB07	YES
UTAH	YES
AZMC	YES
SCAQMD	NO

### Technical Assistance:

Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit [www.benjaminmoore.com](http://www.benjaminmoore.com)

### Technical Data◇

### White

Vehicle Type	Waterbased Acrylic	
Pigment Type	Titanium Dioxide	
Volume Solids	40 ± 1.0%	
Coverage per Gallon at Recommended Film Thickness	Clean Metal 350 - 450 Sq. /Ft. Tight Rust 160 - 220 Sq./Ft.	
Tight Rust	– Wet	7.3 - 10.0 mils
	– Dry	3.0 - 4.0 mils
Clean Metal	– Wet	3.5 – 4.6 mils
	– Dry	1.4 – 1.9 mils
Depending on surface texture and porosity.		
Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	1 Hour
	– To Recoat	4 Hours
	– Cure Time	7 – 10 Days
High humidity and cool temperatures will result in longer dry, recoat and service times.		
Dries By	Coalescence	
Viscosity	85 – 90 KU	
SAG Rating:	Passes 9-10 mils wet (Leneta)	
Flash Point	200 °F or greater (TT-P-141, Method 4293)	
Gloss/Sheen	5 – 10 units @ 60°	
Surface Temperature at Application	– Min.	50 °F
	– Max.	90 °F
Thin With	Clean Water	
Clean Up Thinner	Warm, Soapy Water	
Weight Per Gallon	10.9 lbs.	
Storage Temperature	– Min.	40 °F
	– Max.	95 °F
<b>Volatile Organic Compounds (VOC)</b>		
	199 Grams/Liter	1.66 Lbs./Gallon

◇ Reported values are for White. Contact retailer for values of other bases or colors.

## Acrylic Metal Primer V110

### Surface Preparation

The performance of this product is directly dependent upon the degree of surface preparation employed. All dirt, oils and accumulated salts must be removed prior to employing specific surface preparation methods. SSPC-SP 1 Solvent Cleaning using Corotech V600 Oil & Grease Emulsifier will best accomplish this task.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**Ferrous metals:** All loose rust and mill scale should be removed prior to application of this product. This is best accomplished by abrasive blasting. A minimum of SSPC-SP 6 Commercial Blast is recommended for severe environmental exposures. Small areas may be cleaned in accordance with SSPC-SP 2 Hand Tool Cleaning or SSPC-SP 3 Power Tool Cleaning or SSPC-SP 13 Power Tool Cleaning to Bare Metal. Tightly adhering rust may be coated over provided the surface is intended for use in mild atmospheric exposures.

**Galvanized steel, aluminum and other non-ferrous metals:** Clean bare metal with Corotech V600 Oil & Grease Emulsifier.

**Concrete** should have form release agents and hardening/curing compounds removed prior to coating. This product is not intended for use on floors.

### Application

Mix thoroughly before application. The use of a drill mixer at low speed will best accomplish this task. Should not require thinning, however small amounts of water may be used if necessary.

**Airless Spray:** Tip range between 15 and 19 thousandths. Total fluid output pressure at tip should not be less than 2400 psi.

**Air Spray (Pressure Pot):** DeVilbiss MBC or JGA gun, with 704 or 765 air cap and Fluid Tip E.

**NOTE:** Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with recommended thinner.

**Brush:** Synthetic Bristle. / **Roller:** High quality short nap cover.

**NOTE:** Do not apply if material, substrate or ambient temperature is below 45° F (7.2° C). Relative humidity should be below 90%. Do not apply if within 5 degrees of dew point or if rain is expected within 12 hours of application.

TEST DATA	
Flexibility (ASTM D1737)	Pass 1/8" Mandrel
Dry Heat Resistance	200 °F
Wet Heat Resistance	150 °F
Adhesion (ASTM D3359)	Pass 5B
Salt Spray (ASTM B117) (2 Coats w/1 Topcoat; 1000 Hours)	Rust Breakthrough: 10 Rust Area: 0.01%
Abrasion Resistance (ASTM D4060) CS-17 Wheel, 1000 Cycles, 1000 g Load	100 mg Loss
Accelerated Weathering (ASTM G53) 500 Hours	90% Gloss Retention <0.25 DE Color Change (CMC)

### CHEMICAL RESISTANCE GUIDE (NON-IMMERSION)

Fresh Water	See Finish Coat Data Sheets for Resistance Information.
Salt Water	
Acids	
Alkalis	
Solvents	
Fuel	
Acidic Salt Solutions	
Alkaline Salt Solutions	
Neutral Salt Solutions	

### SYSTEMS RECOMMENDATIONS

#### COMPATIBLE FINISHES

V200 Line, V201, V230 Line, V231 Line, V220 Line, V300 Line, V330 Line, V400 Line, V410, V440 Line, V500 Line, V510 Line, V520 Line, 540 Line, and Other Acrylics, Vinyl Acrylics & Alkyds

V110 Waterborne DTM Metal Primer can be used as a barrier coat on top of older coatings prior to application of high performance coatings with "hotter" solvents, such as 2 component epoxies and urethanes.

For substrates other than listed above, or for usage in severe environmental conditions, please consult with Corotech® Technical Service.

### Clean Up

Clean up with warm, soapy water followed by a clean water rinse.

### Environmental Health & Safety Information

#### Danger

#### May cause cancer

#### Causes damage to organs through prolonged or repeated exposure

**Prevention:** Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Do not breathe dust/fume/mist/vapors/spray. Wash face, hands and any exposed skin thoroughly after handling. Do not eat, drink or smoke when using this product.

**Response:** If exposed or concerned get medical attention.

**Disposal:** Dispose of contents/container to an approved waste disposal plant.



**WARNING** Cancer and Reproductive Harm—  
[www.P65warnings.ca.gov](http://www.P65warnings.ca.gov)

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP FROM FREEZING  
FOR PROFESSIONAL USE ONLY**

**Refer to Safety Data Sheet for  
additional health and safety information.**