



RUST ARRESTOR V180

Features

- Chemically converts rust to inhibit corrosion
- Forms a tight chemical bond to rusted surfaces
- Can be top coated with latex, alkyd, urethane, or epoxy finishes
- Penetrates into tight areas

General Description

Rust Arrestor is a water-based, film-forming primer that chemically transforms rust, halting the corrosion process and enabling the surface to accept a topcoat. When applied over tightly adhering rust, it forms a black, protective film.

Recommended For

Steel & Iron. Corotech® Rust Arrestor is to be applied on tight adhering rusted steel surfaces such as structural steel, angle iron, conveyors, pipes, valves, fittings, duct work, fences, guard rails, wrought iron, grating, equipment, outdoor sign supports and frame work, tanks, etc.

Limitations

- Apply when air and surface temperatures are between 10 °C (50 °F) and 32.2 °C (90 °F).
- Do not apply if rain is threatening.
- Not recommended for immersion service.

Product Information

Colours — Standard:	Technical Data◇	Greenish/Brown Cast
Greenish/Brown cast (00)	Vehicle Type	Latex
— Tint Bases:	Pigment Type	N/A
Do not tint.	Volume Solids	23.0 ± 1.0%
— Special Colours:	Coverage per 3.79 L at	27.9 – 37.2 sq. m.
Contact your retailer.	Recommended Film Thickness	(300 – 400 sq. ft.)
Certifications & Qualifications :	Recommended Film Thickness	– Wet 4.0 - 5.3 mils
The products supported by this data sheet contain a maximum of 100 grams per litre VOC / VOS excluding water & exempt solvents.	– Dry	0.9 - 1.2 mils
This product is compliant as a Primer/Sealer/Undercoater.	Depending on surface texture and porosity.	
Technical Assistance:	Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free 3 Hours
Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-361-5898 or visit www.benjaminmoore.ca		– To Recoat 4 – 6 Hours
		– Full Cure 7 – 10 Days
	High humidity and cool temperatures will result in longer dry, recoat and service times.	
	Dries By	Chemical Reaction
	Viscosity	58 – 62 KU
	Flash Point	Mixed: 93.2 °C (200 °F) or greater (TT-P-141, Method 4293)
	Gloss	5 – 10 @ 60°
	Surface Temperature at Application	– Min. 10 °C (50 °F)
		– Max. 32.2 °C (90 °F)
	Thin With	Not Recommended
	Clean Up Thinner	Water
	Weight Per 3.79 L	4.3 kg (9.5 lbs)
	Storage Temperature	– Min. 7.2 °C (45 °F)
		– Max. 35 °C (95 °F)
	Volatile Organic Compounds (VOC)	
	98 Grams/Litre	

◇ Reported values are for Greenish/Brown cast. Contact retailer for values of other bases or colours.

Rust Arrestor V180

Surface Preparation

Remove loose rust, mill scale, failing paint, dust, dirt and any other surface contaminants by scraping or wire brush. If there is oil or grease on the surface, remove these contaminants by washing the surface with Corotech® V600 Oil & Grease Emulsifier. Rinse thoroughly with clean water and allow it to dry.

IMPORTANT: There must be tight adhering rust present on the surface to be primed or the rust conversion process will not occur. If Corotech® Rust Arrestor turns black (usually within 30 minutes) the conversion process was successful and a top-coat can be applied in 4 to 6 hours. If Corotech® Rust Arrestor does not turn black; allow a minimum of 24 hours dry time before top-coating or “bleeding” may occur.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Shake this product well before beginning the application process. Corotech® Rust Arrestor may be applied by brush, roller or spray. For brush or roller application, pour Corotech® Rust Arrestor into a non-metallic container and apply the product evenly over the tight adhering rusted surface. The product will dry to a black film in about thirty minutes. Do **not** return any unused working material to the original container or contamination of the converter will occur and render the material unusable.

Corotech® Rust Arrestor may be applied by airless, HVLP or conventional spray. Apply the product quickly and clean the equipment immediately after completion. Flush the equipment with clean water, particularly all metal parts coming into contact with the converter.

Apply when air and surface temperatures are between 10 °C (50 °F) and 32.2 °C (90 °F). Do not apply if rain is threatening.

TEST DATA	
Dry Heat Resistance	93.2 °C (200 °F)
Wet Heat Resistance	60 °C (140 °F)
CHEMICAL RESISTANCE GUIDE (NON-IMMERSION)	
Fresh Water	See Finish Coat Data Sheets for Resistance Information.
Salt Water	
Acids	
Alkalies	
Solvents	
Fuel	
Acidic Salt Solutions	
Alkaline Salt Solutions	
Neutral Salt Solutions	

SYSTEMS RECOMMENDATIONS
COMPATIBLE FINISHES
V220 Line, V300 Line, V330 Line, V331 Line, V400 Line, V410, V440 Line, V500 Line, V510 Line, 540 Line, and Other Acrylics & Alkyds

Clean Up

Clean with water.

Environmental Health & Safety Information

WARNING!

Suspected of damaging fertility or the unborn child

Prevention: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required.

Response:

IF exposed or concerned: Get medical advice/attention.

Storage: Store locked up.

Disposal: Dispose of contents /container to an approved waste disposal plant.

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING
FOR PROFESSIONAL USE ONLY**

**Refer to Safety Data Sheet for
additional health and safety information.**