

Features

- Fast 15 minute dry
- No orange peel
- · Airless or HVLP systems
- For all ferrous metal surfaces
- Hard scratch- and impactresistant coating

Recommended For

Properly Prepared and Primed Ferrous & Non-Ferrous Metal.

QUICK DRY GLOSS ENAMEL V230

General Description

Quick Dry Alkyd Enamel is a high-performance, single-component, quick-dry, rust preventive enamel formulated for use on ferrous metal substrates. It provides corrosion resistance for both interior and exterior steel surfaces. Not recommended for non-ferrous metals such as galvanized, aluminum unless properly primed, Quick Dry Alkyd Enamel may be applied to new or properly prepared, rusted surfaces.

Limitations

- Not recommended for non-ferrous metals such as galvanized, aluminum unless properly primed.
- Not recommended for floors or for extreme environments.
- · Not recommended for exterior wood surfaces.
- Not recommended for immersion service or contact with strong solvents.

	Pro	oduct Informa	tion			
Colors — Standard:			Technical Data◊	White		
White (01), Safety Yellow (10), Safety Red (20), Safety Orange (50), Light Gray (71), Battleship Gray (75), Black (80)			Vehicle Type VT All			
			Pigment Type	Titanium Dioxide		
		Volume Solids	51 ± 1.0%			
— Tint Bases: Tintable White (86), Deep Base (87), Clear Base (88).			Coverage per Gallon at Recommended Film Thickness 350 – 450 Sq. Ft.			
Tint with Industrial (844 Type) Colorants Only			Recommended Film Thickness	- Wet 3.6 - 4.6 mils - Dry 1.8 - 2.3 mils		
— Special Colors: Contact your retailer		Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.				
Certification & Qualifications:			Dry Time @ 77 °F (25 °C) @ 50% RH	- Tack Free 15 Minutes - To Recoat* 2 Hours - Full Cure 5 - 7 Days		
The products supported by this data sheet contain a maximum of 400 grams per liter VOC / VOS (3.33 lbs. /gal.)	VOC REGION	COMPLIANT	*Maximum Recoat: Important Recoat Infor	aximum Recoat: See Application Section For contant Recoat Information h humidity and cool temperatures will result in longer		
excluding water & exempt solvents.	FEDERAL	YES				
Masters Painters Institute MPI # 96	OTC	YES	dry, recoat and service times.			
Meets performance of requirements of MIL-P-15090 Type II	OTCII CARB	NO YES	Dries By	Oxidation		
V230-80 meets performance	CARB07	NO NO	Viscosity	75 – 80 KU 50° F (TT-P-141, Method 4293)		
requirements of SSPC Paint #103	UTAH	NO	Flash Point			
Suitable for use in USDA inspected facilities	AZMC	YES	Gloss / Sheen	Gloss (80+ @ 60°)		
raciities	SCAQMD	NO	Surface Temperature at Application	<u>- Min. 50 °F</u> - Max. 100 °F		
Technical Assistance:			Thin With	Do Not Thin		
Available through your local authorized inde			Clean Up Thinner M	Clean Up Thinner Mineral Spirits or High Flash Naphtha		
For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com			Weight Per Gallon	9.7 lbs.		
				– Min. 45 °F		
			Storage Temperature	– Max. 95 °F		
			Volatile Organic Compounds (VOC)			
			395 Grams	s/Liter 3.3 Lbs./Gallon		

 $[\]Diamond$ Reported values are for White. Contact retailer for values of other bases or colors.

Surface Preparation

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, mill scale, form release agents, curing compounds, loose and flaking paint and other surface contaminants.

NEW SURFACES: Steel: For best results, abrasive blast to a commercial blast (SSPC-SP 6). For mild conditions, a hand or power tool cleaning (SSPC-SP 2) may be satisfactory, but performance is dependent upon the degree of surface preparation. The use of a rust inhibitive primer such as V130 QD Alkyd Primer or V131/V132 Universal Primer is recommended.

Previously Painted Surfaces: Wash and rinse any areas that may have oil or grease residue using Corotech V600 Oil & Grease Emulsifier. Dull glossy surfaces by lightly sanding. Remove sanding dust. Remove loose paint. All areas that are rusting, blistering, cracking or peeling must be cleaned to bare metal. If more than 25% of the surface is involved, sandblast the entire surface to a commercial blast and prime. If less than 25% of the surface is involved, clean soiled areas and spot prime.

Galvanized Metal or Aluminum: Apply 1 coat of V110 Acrylic Metal Primer or V175 Waterborne Bonding Primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Mix the product thoroughly before application. The use of a drill mixer at low speed will best accomplish this. Spray application only.

Airless Spray: Tip range between .013 and .017. Total fluid output pressure at tip should not be less than 2200 psi.

Air Spray (Pressure Pot): DeVilbis MBC or JGA gun, with 704 or 765 air cap and Fluid Tip E.

If necessary, small areas can be brushed or rolled using a Natural Brush or a 3/8" lambs wool or 1/4" - 1/2" synthetic roller cover. Roll in one direction, rewet, then cross roll

NOTE: Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with recommended thinner. No reduction is necessary. Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C). Relative humidity should be below 90%. Do not apply if within 5 degrees of dew point or if rain is expected within 12 hours of application.

Maximum Recoat: 18 hrs. (Light sanding required after 18 hrs.) **Full Cure:** 5 – 7 Days

TEST DATA					
Fungal Resistance (TT-P-18)	No Mildew				
Flexibility (ASTM D1737)	Pass ¼" Mandrel				
Dry Heat Resistance	200 °F				
Wet Heat Resistance	150 °F				
Adhesion (ASTM D3359)	Pass 5B				
Salt Fog Resistance (ASTM	200 Hours-Pass (Rating: 10, Rust				
B117) Two coats over V132	Area: 0.00%)				
Line Primer					

CHEMICAL RESISTANCE GUIDE (NON-IMMERSION)				
Fresh Water	Excellent			
2% Sodium Hydroxide	Excellent			
5% Acetic Acid	Excellent			
Lactic Acid	Excellent			
Mineral Oil	Excellent			

SYSTEMS RECOMMENDATIONS							
COMPATIBLE PRIMERS							
					1// /0		

V110 Line, V114, V130 Line, V131 Line, V132 Line, V133 Line, V140 Line, V142 Line, V155 Line, V150 Line, V160 Line, V163 Line, V175, V180 and Other Acrylic and Alkyd Primers

Clean Up

Clean with Mineral Spirits or High Flash Naphtha.

Environmental Health & Safety Information DANGER!

Causes skin irritation

Causes eye irritation

May cause an allergic skin reaction

Suspected of causing cancer

May cause damage to organs

May cause damage to organs through prolonged or repeated exposure

May be fatal if swallowed and enters airways

Highly flammable liquid and vapor

Prevention: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Wash face, hands and any exposed skin thoroughly after handling. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves. Do not breathe dust/fume/mist/vapors/spray. Do not eat, drink or smoke when using this product. Keep away from heat/sparks/open flames/hot surfaces, no smoking. Keep container tightly closed. Ground/bond container and receiving equipment. Use explosion-proof electrical/ventilating/lighting/equipment. Use only non-sparking tools. Take precautionary measures against static discharge.

Response: If exposed or concerned, get medical attention. If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists get medical attention. If skin irritation or rash occurs, get medical attention. If on skin (or hair), take off immediately all contaminated clothing. Rinse skin with water. Wash contaminated clothing before reuse. If swallowed, immediately call a POISON CENTER or physician. Do NOT induce vomiting. In case of fire, use CO2, dry chemical, or foam for extinction.

Storage: Store locked up. Store in a well-ventilated place. Keep cool.

Disposal: Dispose of contents /container to an approved waste disposal plant.

DANGER – Rags, steel wool or waste soaked with the product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container.



WARNING Cancer and Reproductive Harm-

www.P65warnings.ca.gov

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using

KEEP OUT OF REACH OF CHILDREN FOR METAL SUBSTRATES ONLY

Refer to Safety Data Sheet for additional health and safety information.